

Application Number 09/742,625
Response to Office Action mailed September 6, 2007

RECEIVED
CENTRAL FAX CENTER

JAN 07 2008

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application.

Listing of Claims:

Claims 1-36 (Cancelled)

Claim 37 (Currently Amended): A process for the manufacture of polymer coated composite substrate, said process comprising ~~consisting essentially of~~:

providing a compressible mat, wherein the compressible mat comprises at least one of fibers and particles in a resin binder composition;

applying on a surface of the compressible mat a formaldehyde-free, chemically crosslinkable primer coating composition, comprising:

95 to 99 % by weight, based on weight of dry materials in the composition, of an anionically stabilized aqueous emulsion of a copolymer with a T_g of -10 °C to 50 °C, the polymer comprising in polymerized form a polymerization mixture containing two or more ethylenically unsaturated monomers; 0.2 to 5% by weight of a polyimine compound having a number average molecular weight from 250 to 20,000; and 0.2 to 5% by weight of a volatile base;

wherein the chemically crosslinkable composition forms a chemically crosslinked polymer matrix when, or as, the composition is being applied to the compressible mat;

applying on the crosslinked polymer matrix a top coat composition comprising a thermoplastic or a thermosetting polymer latex composition to form a top coat layer; and compressing and heating the crosslinked polymer matrix, the top coat layer, and the compressible mat to form the polymer coated composite substrate.

Claim 38 (Original): The process of claim 37 wherein the compressible mat further comprises a sheet of paper which is glued to the surface of the mat.

Application Number 09/742,625
Response to Office Action mailed September 6, 2007

Claim 39 (Previously presented): The process of claim 38 wherein the crosslinked polymer matrix is formed on the paper.

Claim 40-50 (Cancelled).

Claim 51 (Previously presented): The process of claim 37, wherein the chemically crosslinkable composition has a solids content from about 30% to about 80% by weight.

Claim 52 (Previously presented): The process of claim 37, wherein the chemically crosslinkable composition has a solids content from about 20% to about 70% by weight.

Claim 53-66 (Cancelled).

Claim 67 (Previously Presented): The process of claim 37, wherein the primer coating composition has a pH of about 8 to about 11.

Claim 68 (Previously Presented): The process of claim 37, wherein up to up to 5 wt% of the monomers in the polymerization mixture are α - β -ethylenically unsaturated aliphatic carboxylic acid monomers.

Claim 69 (Previously Presented): The process of claim 37, wherein the monomers comprise (meth)acrylate monomers.

Claim 70 (Previously Presented): The process of claim 37, wherein the volatile base comprises ammonium hydroxide.

Application Number 09/742,625

Response to Office Action mailed September 6, 2007

Claim 71 (Currently Amended): A process for the manufacture of polymer coated composite substrate, said process comprising ~~consisting essentially of~~:

providing a compressible mat, wherein the compressible mat comprises at least one of fibers and particles in a resin binder composition;

applying on a surface of the compressible mat a formaldehyde-free, chemically crosslinkable primer coating composition, comprising:

95 to 99 % by weight, based on weight of dry materials in the composition, of an anionically stabilized aqueous emulsion of a copolymer with a T_g of -10 °C to 50 °C, the polymer comprising in polymerized form a polymerization mixture containing two or more ethylenically unsaturated monomers; 0.2 to 5% by weight of a polyimine compound having a number average molecular weight from 250 to 20,000; and 0.2 to 5% by weight of a volatile base;

wherein the chemically crosslinkable composition forms a chemically crosslinked polymer matrix when, or as, the composition is being applied to the compressible mat;

applying on the crosslinked polymer matrix a top coat composition comprising a thermoplastic or a thermosetting polymer latex composition to form a top coat layer;

compressing and heating the crosslinked polymer matrix, the top coat layer, and the compressible mat to form the polymer coated composite substrate; and

applying a release coat composition on the top coat composition.